



DualCure
lifetime protection

174i2 DUALCURE SX FINISH 90

DualCure products are unique patented high performance finishes. Engineered to provide excellent exterior durability, flexibility and superior adhesion to blasted, primed or e-coated surfaces. This fast curing coating system is designed to provide superior performance and enhanced productivity without the need for heat for drying. 174i2 offers excellent long term protection in moderate to severe environments. Resistant to fresh water, salt water, most chemicals, fumes and spills of mild acids and alkalies. Abrasion and moisture resistant, DualCure finishes are our longest lasting most durable topcoats.

FEATURES

- patented technology NL1034986, US 8889798, EP 2238210, CA 2713534;
- thin film technology;
- cold cure;
- up to 50% CO2 reduction;
- up to 70% VOC reduction;
- quick processing (application and assembling in one day) up to 40% cost reduction;
- >30 years durability in combination with DualCure zinc primer;
- extreme flexibility in combination with extreme abrasion resistance;
- early assembly properties;
- anti graffiti properties; up to 400 MEK rubs resistance
- easy to clean properties; high mar resistance;
- quick drying aspartic topcoat;
- top coat in coating systems for harsh environments (up to and including C5).

WORKING PROCESS

Mixture:	174i2 DualCure SX Finish 90 Base component 2 parts by volume Activator 902V, 1 parts by volume.
Mixing instructions:	Mix base component and activator intensively, preferably using a mechanical mixing device. The temperature of the mixed product should at least be 10°C during application.
Thinning:	The paint can be applied with various spray equipment. The necessary amount of PU5801 depends on used equipment, application method and temperature of the mixed product.
Potlife:	At 20°C 15 minutes (mixed product).
Conditions during application:	The temperature of the substrate should be at least 3°C. above dew point. Keep application area well ventilated during application and drying in order to reduce evaporated solvents. This is necessary to acquire good drying conditions and for the good of the applicators' health.
Method of application	Preferably by means of 2K airless or airmix spray equipment.

PERFORMANCE AND PROPERTIES

Aesthetic product properties

Gloss:	High Gloss
Colour:	Standard colours (e.g. RAL, NCS), lead free.

Product properties:

Volume solids:	± 67 volume % (mixed product)
VOC:	≤ 310 gr/ltr.
Density:	At 20°C ± 1,3 kg/ltr (mixed product)
Dry film thickness:	Standard: 60-100 µm (depends on application process)
Theoretical coverage:	At a dry film thickness of 80 µm 8,30 m ² /ltr.
Practical coverage:	The performance in practice depends on various circumstances. As a guideline for airless spraying: For large dimensions: 70% of the theoretical coverage. For small dimensions: 50% of the theoretical coverage.
Heat resistance	Maximum 80°C (dry load)
Opacity	To achieve best opacity of topcoat some colours need a special shade of primer. Please ask our technical department for advice.

Dry times: at 75% RH and at a standard dry film thickness of 80 µm. (method: BYK Drying recorder)

	15°C
Dust free:	30 minutes
Manageable:	60 minutes
Recoatable:	60 minutes

At a higher dry film thickness longer drying times should be taken in account. During drying and curing the relative humidity should remain between 50-90%. The higher the humidity, the faster the curing.



PROCESSING DATA

	Airless spray	Airmix
Thinner	PU5801	PU5801
Quantity	0-5 vol.%	0-5 vol.%
Nozzle	0,011-0,013 inch	0,011-0,013 inch
Flow pressure	140-200 bar	70-100 bar
Dry film thickness	60-100 µm	60-100 µm

	Airspray
Thinner	PU5801
Quantity	5-10 vol %
Nozzle	2-2,5 mm
Flow pressure	3-4 bar
Dry film thickness	60-100 µm

Cleaning tools: Immediately after application using thinner PU5801.

PRODUCT INFORMATION

Packaging: 20 litre cans and 200 litre drums. Thinner in 25 litre jerry cans and 200 litre drums.

Shelf life: In original well shut packaging 12 months, stored inside at temperatures between 5°C and 40°C.

TEST DATA

Accelerated Weathering: ISO 11507 / ASTM G154 Gloss retention at 60°	2500 hours > 80 %
Saltspray: ISO 9227-NSS / ASTM B 117 Pull off (before/after saltspray): ISO 4624 / ASTM D4541	> 7500 hours (in system C5 combined with 306X) 11,2/11,4 MPa
Flexibility: ISO 1519 / ASTM D522 Cylindrical mandrel ISO 1520 Cupping ISO 6272-2 / ASTM D2794 Reversed impact	10 mm 5,7 mm 2,5 Nm
Abrasion resistance: ASTM D5060 Taber CS-17 / 1kg Loss in weight	4000 rotations 150 mg
Adhesion: ISO 4624 Pull-off on Sa2½	10 MPa
Chemical resistance: MEK rub-test, double rubs gloss retention at 60°	100 > 80%

ENVIRONMENT AND HEALTH

Labelling: In accordance with EU directions 67/548/EEG and in accordance with directives on hazardous materials. Harmful and irritating in contact with skin, eyes and by inhalation. In case of eye contact, immediately wash with large amounts of water and contact a medical expert. Do not eat, drink or smoke during application.

UN: 1263

Aware code 18-IV

AWARE

The AWARE (acronym for Adequate Warning and Air Requirement) is a coding system for products containing volatile organic compounds (VOC), a tool for product manufacturers to support risk assessment and product innovation. Additionally it can be used for hazard communication with end-users to inform them about potential health risks of hazardous products. The system is based on the Norwegian concept for the OAR (Occupational Air Requirement) and the Danish concept for the MAL-code system. The AWARE code consist of two digits separated by a hyphen. Both digits are elaborated based on physical-chemical considerations and adapted to the European Dangerous Preparations Directive. The first digit is expressed as m3 required fresh air at the workplace to dilute the emissions from one litre used product to be sure not to exceed the level of the Occupational Exposure Limit (OEL). It is based on the component content, vapour pressure, solubility and toxicity. The second digit is derived from R phrases ascribed to the substances in the product. In this way the AWARE is a tool that can be used for risk identification of products as well as ingredients in products. A higher AWARE does indicate a higher risk. It is a perfect tool to support substitution of hazardous products.

PRE-TREATMENT

Preliminary treatment, steel untreated:

The surface needs to be pretreated according ISO12944 part 4 § 6.2.3. Remove grease, oil, dirt etc. using an appropriate cleansing agent, for instance ENVICLEAN PR (for use see product sheet) and a high pressure spraying pistol. Grit blasting to purity degree Sa 2½ in accordance with ISO 8501-1. After blasting remove all dust from the entire surface with compressed air which is free of moisture and grease. Apply first coating layer within 6 hours. In case the final coating layer is applied on the construction site, extra precautions need to be taken.

PROTECTIVE COATINGS

Our 'protective coatings' excel by virtue of their durability, flexibility, adhesion, easy application, anti-corrosion, and chemical and mechanical resistance. This is the result of our vast competence in coating chemistry, combined with a good eye for our client's requirements and wishes. The coating systems conform to ISO 12944 and comply with international VOC guidelines.

TOUCH UP

Touching up of damages or untreated parts at the construction site. Remove grease, oil, dirt etc. using an appropriate cleansing agent, for instance ENVICLEAN PR (for use see product sheet). Remove the rust from all mechanical damage caused by transport and mounting, untreated welding strips and welding spots and burns with rotating steel wire brushes, sanding discs or steel wire brushes and coarse sandpaper to purity degree St3, in accordance with ISO 8501-1.

Smooth the transition of cleansed parts to parts with intact coats of paint by sanding and scraping.

After sanding, remove all dust from the entire surface with compressed air which is free of moisture and grease. Then touch up the object with the entire paint system, as described in this paint advice.

Touch up light surface damages only with the product of the top coat, as described in the paint advice.

MAINTENANCE

It is recommended to clean the surface regularly and to inspect the coats of paint for defects annually. Touch up any defects with the original paint system.

TECHNICAL SUPPORT

Baril Coatings B.V. offers more than just advice. We offer a total service solution to the principal, the architect, the main contractor and the painting contractor.

In order to ensure the required performance in terms of durability, Baril Coatings offers full technical support and supervision during implementation and completion of the application process, all in accordance with the ISO 12944 guideline.

The supervision and support provided by Baril Coatings does not relieve the painting contractor of his responsibility for the work carried out by him. The painting contractor must thoroughly familiarize himself with the most recently updated product data sheets and the general terms and conditions of Baril Coatings for protective coatings on steel. Baril Coatings is not responsible for application and the application conditions. The final durability depends mainly on factors that are outside our control and for that reason we cannot accept any liability.

WARRANTY & DISCLAIMER

This Product Data Sheet supersedes those previously issued. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to our UNIFORM CONDITIONS OF SALE AND DELIVERY FOR PAINT, PRINTING INK AND OTHER PRODUCTS unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said UNIFORM CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice.

